



[Previous abstract](#) | [Graphical version](#) | [Text version](#) | [Next abstract](#)

Session SC05 - Magnetoresistance IX: Tunnelling and Transport in Manganites.

ORAL session, Wednesday afternoon, March 24

Room 367W, GWCC

[SC05.03] Magnetic percolation and giant spontaneous Hall effect in $\text{La}_{1-x}\text{A}_x\text{CoO}_3$ ($\text{A} = \text{Ca}, \text{Sr}, 0.1 \leq x \leq 0.5$)

N.-C. Yeh, A. V. Samoilov, C. C. Fu, G. Beach (Department of Physics, California Institute of Technology), R. P. Vasquez (Center for Space Microelectronics Technology, Jet Propulsion Laboratory, California Institute of Technology, Pasadena, CA 91109)

The spontaneous Hall effect and magnetoresistance (ΔR_H) of $\text{La}_{1-x}\text{A}_x\text{CoO}_3$ ($\text{A} = \text{Ca}, \text{Sr}$) are investigated as a function of the doping level x . We find that the Hall resistivity ρ_{xy} of the ferromagnetic cobaltites at $T < T_{\text{Curie}}$ is proportional to the magnetization M of the sample, and that for both $\text{La}_{1-x}\text{Ca}_x\text{CoO}_3$ and $\text{La}_{1-x}\text{Sr}_x\text{CoO}_3$, the spontaneous Hall coefficient R_s ($\text{equiv } \rho_{xy}/M$) is a strong function of the temperature T and the doping level, reaching maximum slightly below T_{Curie} for each doping level, and achieving the largest magnitude near the magnetic percolation threshold $x \sim 0.2$. In the case of $\text{La}_{0.8}\text{Ca}_{0.2}\text{CoO}_3$, we obtain a record value of $R_s \approx 1400 \times 10^{-9} \text{ m}^3/\text{C}$, exceeding all spontaneous Hall coefficients of known single-phased ferromagnets. In contrast, the longitudinal resistivity of these cobaltites decreases monotonically with increasing magnetic field for all samples, except $\text{La}_{0.8}\text{Ca}_{0.2}\text{CoO}_3$ that exhibits non-monotonic dependence. The giant spontaneous Hall effect may be attributed to the enhanced spin fluctuations near T_{Curie} , and the strong spin-orbit scattering from percolating high-spin $\text{Co}^{3+} - \text{Co}^{4+}$ conducting clusters in a low-spin Co^{III} non-conducting matrix. Possible correlation between ΔR_H and ρ_{xy} will be discussed.

■ Part 5 of program listing